

M multinuclear Solid-State NMR Study of Local Structure and Dynamics in $\text{Li}_{0.7}\text{Nb}_3\text{S}_4$

K. Volgmann,^{1,2} V. Epp,³ P. Bottke,³ C. V. Chandran,^{1,2} S. Nakhal,⁴
M. Lerch,⁴ M. Wilkening,³ P. Heitjans^{1,2}

¹Institut für Physikalische Chemie u. Elektrochemie, Leibniz Universität Hannover,
Callinstr. 3 – 3a, D-30167 Hannover, Germany

²Zentrum für Festkörperchemie und Neue Materialien (ZFM), Leibniz Universität Hannover,
Callinstr. 3 – 3a, D-30167 Hannover, Germany

³Institut für Chemische Technologie von Materialien, Technische Universität Graz,
Stremayrgasse 9, A-8010 Graz, Österreich

⁴Institut für Chemie, Technische Universität Berlin, Straße des 17. Juni 135,
D-10623 Berlin, Germany

Corresponding author: Paul Heitjans, E-Mail: heitjans@pci.uni-hannover.de

Solid-state nuclear magnetic resonance (NMR) spectroscopy is capable of giving insights into the diffusivity of, *e.g.*, Li ions on the microscopic scale. Standard methods of solid-state NMR such as lineshape analyses and spin-lattice relaxation measurements have repeatedly been applied also to sulfides, *e.g.*, Li_xTiS_2 . Besides Li_xTiS_2 which was studied by NMR both in its hexagonal and cubic modification [1-4], measurements on layer-structured $\text{Li}_{0.7}\text{NbS}_2$ were also done [5].

The present work focuses on channel-structured $\text{Li}_{0.7}\text{Nb}_3\text{S}_4$ [6], where, among others, the question of the dimensionality of the diffusion pathway arises. Insights into the local structure are given by ^6Li , ^7Li , ^{33}S and ^{93}Nb NMR spectra. ^6Li and ^7Li NMR spectra show one mobile Li species as it could be expected from the crystal structure. Li ion dynamics are investigated by means of ^7Li NMR spin-lattice relaxation (SLR) and spin-alignment echo (SAE) decay measurements. Results from SLR NMR in the rotating frame of reference T_{1p} (Fig. 1) and SAE yield Li jump rates over several decades. The Arrhenius parameters, *i.e.* the pre-exponential factor and the activation energy, obtained from the fit show that the Li diffusivity is much slower in $\text{Li}_{0.7}\text{Nb}_3\text{S}_4$ than in $\text{Li}_{0.7}\text{NbS}_2$ [5].




Fig. 1: ^7Li NMR SLR rate $1/T_{1p}$ ($\omega_1/2\pi = 20$ kHz) in $\text{Li}_{0.7}\text{Nb}_3\text{S}_4$ vs. inverse temperature. The SLR background rate follows a power law. The diffusion-induced SLR rate peak shows up at $T \approx 500$ K.

References

- [1] W. Küchler, P. Heitjans, A. Payer, R. Schöllhorn, *Solid State Ionics* **70/71** (1994) 434-438
- [2] M. Wilkening, W. Küchler, P. Heitjans, *Phys. Rev. Lett.* **97** (2006) 065901/1-4
- [3] M. Wilkening, P. Heitjans, *Phys. Rev. B* **77** (2008) 024311/1-13
- [4] C. Vinod Chandran, S. Nakhal, K. Volgmann, E. Witt, M. Lerch, P. Heitjans, *this conference*
- [5] V. Epp, S. Nakhal, M. Lerch, M. Wilkening, *J. Phys.: Condens. Matter* **25** (2013) 195402/1-7
- [6] A. F. J. Ruysink, F. Kadijk, A. J. Wagner, F. Jellinek, *Acta Cryst.* **B24** (1968) 1614-1619